



Recycling marine plastics into 3D printer filament.

Extended Technical Data Sheet (updated 15th November 2019)

Product Name - Porthcurno

Material - Recycled Nylon 6, Polyamide 6, PA 6

Description

Porthcurno is a semi-amorphous nylon blend with high tensile strength, good impact resistance and low surface friction.

Its properties after atmospheric curing or overnight soaking in water make an especially interesting material for use in applications where moderate flexibility and high strength are useful e.g. in-production fittings, wearables and live hinges.

Nylon is a technical, engineering grade material and is not recommended for novice users.

As with most nylons, Porthcurno is susceptible to absorption of moisture both before and after forming.

Porthcurno should be dried prior to use and kept in a controlled environment between uses. Insufficient drying prior to use will result in warping, poor surface quality and an increased probability of failure.

Typical drying parameters are 5 hours at 80°C at a controlled humidity of 10% H₂O or lower. Effective drying cannot be achieved reliably at temperatures below 70°C.

Test	Test Standard	SI Unit	Measured Value	Standard Deviation
Density	ISO 1183	kg/m ³	1127	7
Water Absorption	40°C for 28 Days	%	9.12	
Wear Resistance	Taber Abrasion H22/3000 cycles	%	0.02	0.01
Resistance to UV -28 Days				
Tensile Strength @ Break	ISO 527-2	Mpa	42	4
Elongation @ Break	ISO 527-2	%	22	10
Tensile Modus	ISO 527-2	Mpa	1280	379

DISCLAIMER

Properties reported here are average of typical batches examined by an independent ISO certified laboratory. Any technical information or assistance provided herein is given and accepted at your own risk, and neither Fishy Filaments nor its affiliates make any warranty relating to it or because of it. Neither Fishy Filaments nor its affiliates shall be responsible for the use of this information, or of any product, method or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made regarding the merchantability or fitness of any product; and nothing herein waives any of Fishy Filaments's conditions of sale.

Typical IM Parameters

Mold Temperature	<40°C
Injection Temperature	225 °C
New Polymer	5% (95% Porthcurno)

Test	Test Standard	SI Unit	Measured Value at 23C	Standard Deviation	Measured Value at 60C	Measured Value at 90C	Measured Value at 120C	Measured Value at 150C
Tensile Strength								
Tensile Strength @ Break	ISO 527-2	Mpa	48	6	40	29	26	23
Elongation @ Break	ISO 527-2	%	3.6	1.2	58	-	-	-
Tensile Strength @ Yield	ISO 527-2	Mpa	59	2				
Elongation @ Yield	ISO 527-2	%	41	18				
Tensile Modus	ISO 527-2	Mpa	2262	208	638	559	368	279
Flex (3 Point)								
Flexural Stress	ISO 178	Mpa	70	2				
Flexural Modulus	ISO 178	Mpa	2126	184				
Charpy Impact								
Charpy Impact at -20C	ISO180	kJ/m ²	2.76	0.54				
Charpy Impact at +23C	ISO180	kJ/m ²	5.15	0.72				
Heat & Flammability								
VICAT	ISO306/B120	C	195.4	0.2				
Heat Distortion temperature	ISO 75/A/ 1.8MPa	C	53.4	0.1				
Melting Temperature	ISO 11357-3	C	220					
Thermal Expansion	ISO 11359	µm/m°C	105.3					
Flammability	UL94 Vertical test	V0,1 or 2	V0					